

**Listing of Claims**

1. (Currently Amended) A method for making a glass product from cracked laminated glass, comprising stacking two or more pieces of the laminated glass, and heating the-laminated glass to:  
  
burn out a plastic interlayer in the laminated glass, and  
  
fuse glass in the laminated glass to form the glass product,  
  
wherein the glass product has a pattern corresponding to cracks present in the laminated glass prior to heating.
2. (Previously Amended) The method according to claim 1, wherein the laminated glass comprises laminated-glass-waste, including but not limited to windshield or safety-glass waste.
3. (Currently Canceled) ~~The method according to claim 1, wherein the laminated glass comprises cracked glass held together by a plastic interlayer.~~
4. (Previously Presented) The method according to claim 1, further including breaking the laminated glass to form cracked glass held together by a plastic interlayer, prior to the heating.
5. (Previously Amended) The method according to claim 1, further including cutting the laminated glass into a shape, including but not limited to a square, rectangle, triangle, polygon, circle, or oval shape, prior to the heating.
6. (Previously Presented) The method according to claim 1, further including applying a coating to the laminated glass, prior to the heating.
7. (Previously Presented) The method according to claim 1, further including applying a

glaze, enamel, metal foil, thick-film paste, thin-film layer, or powder to the laminated glass, prior to the heating.

8. (Previously Canceled) ~~The method according to claim 1, further including stacking two or more pieces of laminated glass, prior to the heating.~~

9. (Previously Presented) The method according to claim 1, further including:

selecting pieces of the laminated glass to provide pieces of uncoated laminated glass, applying a coating to one or more pieces of the laminated glass to form pieces of coated laminated glass, and

stacking two or more pieces of laminated glass, selected from the pieces of coated laminated glass and the pieces of uncoated laminated glass, prior to the heating.

10. (Previously Presented) The method according to claim 1, further including:

selecting pieces of the laminated glass to provide pieces of uncoated laminated glass, applying a glaze, enamel, metal foil, thick-film paste, thin-film layer, or powder to one or more pieces of laminated glass to form pieces of coated laminated glass, and stacking two or more pieces of laminated glass, selected from the pieces of coated laminated glass and the pieces of uncoated laminated glass, prior to the heating.

11. (Previously Presented) The method according to claim 1, wherein the heating comprises a maximum temperature of about 700°C to about 900°C.

12. (Previously Amended) The method according to claim 1, wherein the glass product is

further processed by one or more additional steps, ~~including but not limited to~~ comprised of cutting, polishing, grinding, tumbling, etching, sand blasting, applying a coating, or reheating.

13. (Previously Canceled) ~~The method according to claim 1, wherein the glass product has a~~

~~pattern corresponding to cracks present in the laminated glass prior to heating.~~

14. (Previously Presented) The method according to claim 1, wherein the glass product has

one or more of the following characteristics:

a coating on an interior portion of the glass product,

a coating on an exterior surface of the glass product,

a glossy surface appearance on the glass product,

a textured surface appearance on the glass product,

a matte surface appearance on the glass product,

a transparent appearance in the glass product,

a translucent appearance in the glass product,

an opaque appearance in the glass product,

an interior or exterior coating to reflect light and/or heat from the glass product, and

an interior or exterior coating to absorb light and/or heat in the glass product.

15. (Previously Presented) The method according to claim 1, wherein the glass product

comprises wall tile, floor tile, roof tile, windowpanes, countertops, sinks, tabletops, or dinnerware.

16. (Currently Amended) A method for making a glass product from cracked laminated glass,

comprising:

cutting the laminated glass into pieces,

stacking two or more of the pieces to form a stack, and

heating the stack to form the glass product,

wherein the glass product has a pattern corresponding to cracks present in the laminated glass prior to heating.

17. (Previously Amended) The method according to claim 16, wherein the laminated glass comprises ~~laminated glass waste, including but not limited to~~ windshield or safety-glass waste.
18. (Currently Canceled) ~~The method according to claim 16, wherein the laminated glass comprises cracked glass held together by a plastic interlayer.~~
19. (Previously Presented) The method according to claim 16, further including breaking the laminated glass, before or after the cutting, to form cracked glass held together by a plastic interlayer.
20. (Previously Amended) The method according to claim 16, wherein the pieces comprise a ~~shape, including but not limited to~~ a square, rectangle, triangle, polygon, circle, or oval shape.
21. (Previously Presented) The method according to claim 16, further including applying a coating to one or more of the pieces.
22. (Previously Presented) The method according to claim 16, further including applying a glaze, enamel, metal foil, thick-film paste, thin-film layer, or powder to one or more of the pieces.
23. (Previously Presented) The method according to claim 16, wherein the heating comprises:  
burning out a plastic interlayer in the laminated glass, and  
fusing glass in the laminated glass to form the glass product.
24. (Previously Presented) The method according to claim 16, wherein the heating comprises a maximum temperature of about 700°C to about 900°C.
25. (Previously Amended) The method according to claim 16, wherein the glass product is further processed by one or more additional steps, ~~including but not limited to~~ comprised

of cutting, polishing, grinding, tumbling, etching, sand blasting, applying a coating, or reheating.

26. (Previously Canceled) ~~The method according to claim 16, wherein the glass product has a pattern corresponding to cracks present in the laminated glass prior to heating.~~

27. (Previously Presented) The method according to claim 16, wherein the glass product has one or more of the following characteristics:

- a coating on an interior portion of the glass product,
- a coating on an exterior surface of the glass product,
- a glossy surface appearance on the glass product,
- a textured surface appearance on the glass product,
- a matte surface appearance on the glass product,
- a transparent appearance in the glass product,
- a translucent appearance in the glass product,
- an opaque appearance in the glass product,
- an interior or exterior coating to reflect light and/or heat from the glass product, and
- an interior or exterior coating to absorb light and/or heat in the glass product.

28. (Previously Presented) The method according to claim 16, wherein the glass product comprises wall tile, floor tile, roof tile, windowpanes, countertops, sinks, tabletops, or dinnerware.